



PRODUCT DATA SHEET
AWLCRAFT® 2000 ACRYLIC URETHANE TOPCOAT
 (Code numbers can be found on Suggested List Price Schedule or Color Card)

Features & Uses

Awlcraft 2000 is a two component, fast drying acrylic urethane coating with long lasting gloss and color retention. Provides an easy to apply, buffable finish. Spray application only. Do not use below the waterline. Awlcraft 2000 is also available in a range of metallic colors (refer to separate datasheet).

Specification Data

Type: Two Component Acrylic Urethane
 Color: See Color Card and/or your Awlmix distributor.
 Packaging: Available in 1 gallon and 1 quart containers
 Theoretical Coverage: Sq. Ft./Gallon; 573 Sq. Feet (53m²) at one mil dry (25 microns); 230 Sq. Feet (21m²) at recommended dry film thickness
 Calculated for mixed base and converter, reduced 25%.
 Coverage calculations are based on theoretical transfer efficiency of 100%. Actual coverage rate obtained will vary according to equipment choice, application techniques, part size, and application environment.
 Recommended Wet Film Thickness: 6-9 mils (150-225 microns) total of 3 or more coats.
 Recommended Dry Film Thickness: 2-3 mils (50-75 microns) total of 3 or more coats.
 Anticipated Cure Time at 77°F, 50% R.H: 24 Hours to tape free; 3 days to light service; 14 days for full cure.
Recoatability: Typical spray applications consist of two to three coats applied over 1-4 hours. Exact time will vary with temperature, project size, and film thickness applied. AWLCRAFT 2000 topcoats which have been allowed to cure more than 24 hours must be sanded before recoating.

VOC: Base: 472.5 g/ltr or 3.9 lbs/gallon
 Spray Converter (G3010) 591g/ltr or 4.9 lbs/gallon

Product Components, Reducers, Additives and Auxiliary Components

AWLCRAFT 2000 Topcoat Base	(Number from the Stock List)
High Gloss Clear	F3029
AWLCAT #2 Spray Converter	G3010
Standard Reducer-Spray	T0003
Fast Evaporating Reducer-Spray	T0001
Very Fast Evaporating Reducer-Spray	T0002
Hot Weather Reducer-Spray	T0005
PRO-CURE Accelerator X-98	73014
PRO-CURE Accelerator X-138	73015
CRATER-X	M1017
GRIPTEX Non-Skid Particles-Fine	73012
GRIPTEX Non-Skid Particles-Coarse	73013
Flattening Agent	G3013
Equipment Cleaning	T0001, T0002 or T0003 Reducers or M.E.K.

Application Equipment

Conventional air atomized spray or HVLP spray.

1 East Water Street • Waukegan, Illinois 60085 • USA • Tel: 847.599.6212 • Fax: 847.599.6209
 Bannerlaan 54 • B-2280 Grobbendonk • Belgium • Intl. Tel: 32.14.257770 • Intl. Fax: 32.14.230880
 76 Waterway Drive • Coomera • QLD 4209 • Australia • Tel: 61.7.5573.9655 or 1800.007.866 • Fax: 61.7.5573.9677
 686 Rosebank Road • Avondale • Auckland • New Zealand • Tel: 64.9.828.3009 or 0800.150.527 • Fax: 64.9.828.1129
 No.1 Tuas Avenue 4 • Singapore 639382 • Tel: 65.6862.2928 • Fax: 65.6862.0778



PRODUCT DATA SHEET
AWLCRAFT® 2000 ACRYLIC URETHANE TOPCOAT
(Code numbers can be found on Suggested List Price Schedule or Color Card)

SPRAY EQUIPMENT:

Pressure Pot System:

Devilbiss or equivalent:
Spray Gun: JGA type
Fluid Nozzle: AV-645-FX
Fluid Needle Size: 1.1
Fluid Flow Rate: 170 - 270 ml/min
Air Nozzle: AV-4239-43
GUN PSI: 2.5 – 3.5 bar (36-51 psi)

Cup Gun System:

Devilbiss or equivalent:
Spray Gun: JGA type
Fluid Nozzle: AV-4239-43
Fluid Needle Size: 1.1
Air Nozzle: AV-4239-43
GUN PSI: 2.0 – 3.0 bar (29-44 psi)

Surface Preparation

Best results are achieved when sprayed over properly prepared AWLGRIP® 545 Epoxy Primer. May be applied directly over some existing finishes. The existing finish must be sound, tightly adhered to the substrate, and chemically compatible with AWLCRAFT 2000

Mixing and Reduction

Spray: Mix by volume two parts AWLCRAFT 2000 Topcoat Base Component with one part AWLCAT #2/G3010 Spray Converter to a smooth, homogenous mixture. Reducer addition level required to achieve 14 seconds viscosity (DIN4 or equivalent) varies color to color. For standard conventional spray application this can be attained by adding up to 25% reducer using the correct spray reducer(s) appropriate for conditions. For example, if a 25% reduction is used, overall mix is 2:1:¼ by volume (8 oz. Base, 4 oz. G3010, 3 oz. Reducer).

Clear coats and painting in high temperature conditions may require additional reduction.

Application Instructions

General: The primed surface must be clean and dry. Achieving maximum gloss and distinction of image requires the primer be smooth sanded with 320 grit paper before topcoat application. Using a contrasting mist coat of lacquer primer as a “guide coat” is recommended. Smooth sanding until all the “guide coat” is removed indicates a texture free surface.

Three coats are recommended for spray applications.

Spray application: Apply a light, smooth, slightly wet tack coat to the surface. Allow tack coat to “flash off” 15- 45 minutes. Allow the second coat to “flash off” 30-45 minutes until only slightly tacky before applying the third coat. Coats two and three are not “full, wet” coats. The second coat is a slightly heavy tack coat with the third coat just wet enough to obtain full hide (opacity) or color coverage. More than 3 coats may be required to achieve full hide (opacity) or color coverage.

Warning:

Do not apply paint materials to surfaces less than 5°F (3°C) above dew point, or to surfaces warmer than 105°F (41°C). Ambient temperature should be minimum 55°F (13°C) and maximum 105°F (41°C).

1 East Water Street • Waukegan, Illinois 60085 • USA • Tel: 847.599.6212 • Fax: 847.599.6209
Bannerlaan 54 • B-2280 Grobbendonk • Belgium • Intl. Tel: 32.14.257770 • Intl. Fax: 32.14.230880
76 Waterway Drive • Coomera • QLD 4209 • Australia • Tel: 61.7.5573.9655 or 1800.007.866 • Fax: 61.7.5573.9677
686 Rosebank Road • Avondale • Auckland • New Zealand • Tel: 64.9.828.3009 or 0800.150.527 • Fax: 64.9.828.1129
No.1 Tuas Avenue 4 • Singapore 639382 • Tel: 65.6862.2928 • Fax: 65.6862.0778



PRODUCT DATA SHEET
AWLCRAFT® 2000 ACRYLIC URETHANE TOPCOAT
(Code numbers can be found on Suggested List Price Schedule or Color Card)

The information in this Product Data Sheet is not intended to be exhaustive. Any person using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk and, to the extent permitted by law, we can accept no responsibility for the performance of the product or for any loss or damage arising out of such use. The information contained in this Product Data Sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Awlgrip® and all products mentioned in this Product Data Sheet are trademarks of, or licensed to, Akzo Nobel.

© Akzo Nobel, 2009

1 East Water Street • Waukegan, Illinois 60085 • USA • Tel: 847.599.6212 • Fax: 847.599.6209
Bannerlaan 54 • B-2280 Grobbendonk • Belgium • Intl. Tel: 32.14.257770 • Intl. Fax: 32.14.230880
76 Waterway Drive • Coomera • QLD 4209 • Australia • Tel: 61.7.5573.9655 or 1800.007.866 • Fax: 61.7.5573.9677
686 Rosebank Road • Avondale • Auckland • New Zealand • Tel: 64.9.828.3009 or 0800.150.527 • Fax: 64.9.828.1129
No.1 Tuas Avenue 4 • Singapore 639382 • Tel: 65.6862.2928 • Fax: 65.6862.0778